



## **Chemical Composition**

Symbol	Typical	Guarantee
K <sub>2</sub> O	22.2 %	22% Minimum
Mg	11.6 %	10.8% Minimum
S	22.5 %	22% Minimum
Cl	1.4 %	2.5% Maximum
H <sub>2</sub> O	0.12 %	
	K <sub>2</sub> O Mg S Cl <sup>-</sup>	K2O 22.2 %   Mg 11.6 %   S 22.5 %   Cl <sup>-</sup> 1.4 %

## Particle Size Distribution Cumulative %

Tyler Mesh	US Mesh	Opening (mm)	Typical Range	Typical
4	4	4.75	0 - 2	1
5	5	4.00	5 - 25	15
6	6	3.35	15 - 50	30
7	7	2.80	30 - 70	48
8	8	2.36	45 - 85	66
9	10	2.00	65 - 95	82
10	12	1.70	85 - 100	94
12	14	1.40	95 - 100	99

Physical Properties				
Parameter	Typical			
Bulk Density (Loose)				
- lb/ft³	88			
- kg/m³	1412			
Angle of Repose	34 Degrees			

## Sizing CharacteristicsParameterTypicalSize Guide Number (SGN)275Uniformity Index (UI)40

## Please refer to the Safety Data Sheet (SDS #: MOS100042) for additional information (www.mosaicco.com)

The information contained in this data sheet is a representation of the average properties of product analyses as tested on composite samples and typical analyses should not be considered a guaranteed specification. Individual shipment and grab sample analyses may fall outside of the above typical values Additional handling, transportation, or improper/extended storage may affect product analyses. Mosaic disclaims any responsibility or liability for any loss or damage that may occur from any reliance on, or other use of, the above information with respect to the product.